

### **Ferrite Plates for Wireless Charging**

MP & 33 Series



### FEATURES ROHS






- Ferrite materials are Wireless Power Consortium(WPC) listed, recommended & certified for interoperability test
- Optimized for highest charging efficiency
- Precise dimension control and automotive grade available
- -40°C to 125°C operating temperature
- Available in wide range of size selection, custom shapes are also available

#### **APPLICATIONS**

- Wireless charger for general consumer electronics,transmitter(TX) or receiver(RX)
- Aftermarket charging pads
- Wireless charger for Office, Residential, and Public Area applications
- Wireless charger embedded solution for automobile central console, arm-rest...ect.
- Power tools or any industrial devices that need power transmission without metallic contact

#### **DIMENSIONS**

PART NUMBER	A mm (inches)	B mm (inches)	C mm (inches)	Fig #
MP1040-3M0	26.42	26.42	2.25	1
	(1.040)	(1.040)	(0.089)	'
MP1496-0M0	38.00	38.00	2.00	1
	(1.496)	(1.496)	(0.079)	'
MP2106-0M0	53.00	53.00	2.50	1
	(2.087)	(2.087)	(0.099)	'
MP2126-0M0	53.80	53.80	1.10	1
	(2.118)	(2.118)	(0.043)	'
MP2170-1M0	47.20	55.20	2.50	1
	(1.858)	(2.173)	(0.099)	'
MP3940-0M0	100.00	56.00	1.10	1
	(3.937)	(2.205)	(0.043)	'
33P2098-0M0	53.30	53.30	2.50	1
	(2.099)	(2.099)	(0.099)	'
33P3839-0M0	97.50	50.00	1.10	2
	(3.839)	(1.969)	(0.043)	2



USA: +1.423.308.1690 Europe: +42.0.4885.7511.1 Asia: +86.757.2563.8860

MCP-DS-PLATES REV1.1 0714



## **Ferrite Plates for Wireless Charging**

MP & 33 Series


#### PART NUMBER SYSTEM EXAMPLE


<u>33</u>	<u>P</u>	<u>2098</u> -	<u>0M0</u>	
M-28 Material	Plate	Part Size Code	Thickness Code	
33-33 Material			Catalog or Custom Information	

#### **MATERIAL SPECIFICATIONS**


Property	Symbol	Unit	28 Material (WPC Listed)	33 Material
Initial Permeability	$\mu_{i}$		650	2300
Flux Density	В	mT [Gauss]	280 [2800]	390 [3900]
@ Field Strength	Н	A/m [Oe]	800 [10]	800 [10]
Residual Field Strength	$B_r$	mT [Gauss]	130 [1300]	55 [550]
Coercive Strength	$H_c$	A/m [Oe]	32 [0.4]	9 [0.1]
Loss Foster @ Fraguensy	tan δ/μ <sub>i</sub>	$10^{-6}$	500	6
Loss Factor @ Frequency	f	MHz	0.1	0.1
Curie Temperature	$T_c$	°C	> 140	> 200
Resistivity	ρ	Ω-cm	10 <sup>5</sup>	5x10 <sup>2</sup>


# TYPICAL ELECTRICAL CHARACTERISTICS 28 MATERIAL





#### 33 MATERIAL





USA: +1.423.308.1690 Europe: +42.0.4885.7511.1 Asia: +86.757.2563.8860

#### MCP-DS-PLATES REV1.1 0714

Any information furnished by Laird Technologies, inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies materials or products for any specific or general uses. Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any link. All Laird Technologies products are sold pursuant to the Laird Technologies. Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2014 Laird Technologies, linc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies op, and other marks are trademarks or registered trademarks of Laird Technologies, the are an affiliate company thereof. Other product or service names may be the property of third parties, Nothing herein provides as license under any Laird Technologies or any third party intellectual property of into April 100 property of the April 100 provides a decrease under any Laird Technologies or any third party intellectual property of the April 100 property of th